


A7 D2
A Dobena



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 138 794 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
04.10.2001 Bulletin 2001/40

(51) Int Cl.7: **C22C 21/06, C22C 21/08**

(21) Application number: **01200977.5**

(22) Date of filing: **15.03.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **31.03.2000 EP 00201156**
20.10.2000 EP 00203660

(71) Applicants:
• **Corus Aluminium Voerde GmbH**
46562 Voerde (DE)
• **Corus Aluminium Walzprodukte GmbH**
56070 Koblenz (DE)

(72) Inventors:
• **Spanjers, Martinus Godefridus Johannes**
2331 HV Leiden (NL)

• **Haszler, Alfred Johann Peter**
56179 Vallendar (DE)
• **Sampath, Desikan**
56070 Koblenz (DE)

(74) Representative: **Hansen, Willem Joseph Maria**
Corus Technology BV
Corus Intellectual Property Department
PO Box 10000
1970 CA IJmuiden (NL)

Remarks:

A request for correction of the description has been filed pursuant to Rule 88 EPC. A decision on the request will be taken during the proceedings before the Examining Division (Guidelines for Examination in the EPO, A-V, 3.).

(54) **Aluminium die-casting alloy**

Al - Druckguss-Legierung !

(57) The invention relates to an aluminium-magnesium alloy for casting operations consisting of, in weight percent, Mg 2.7-6.0, Mn 0.4-1.4, Zn 0.10-1.5, Zr 0.3 max., V 0.3 max., Sc 0.3 max., Ti 0.2 max., Fe 1.0 max.,

Si 1.4 max., balance aluminium and inevitable impurities. The casting alloy is particularly suitable for application in die-casting operations. Further the invention relates to the use of the casting alloy for die-casting automotive components.

EP 1 138 794 A1

Description

[0001] The invention relates to an aluminium-magnesium alloy for casting operations and to the use of this aluminium-magnesium alloy in casting operations, in particular in die-casting operations. Further the invention relates to the application of the AlMg casting alloy in automotive components.

[0002] Conventional aluminium-magnesium casting alloys have many attractive properties, such as high ultimate tensile strength (>170 MPa) and elongation (>8 %) with moderate yield strength (>120 MPa). However, there is a demand for aluminium cast alloys combining improved mechanical properties with a good corrosion resistance.

[0003] Some disclosures of aluminium-magnesium casting alloys found in the prior art literature will be mentioned below.

[0004] WO-96/15281 discloses a casting alloy consisting of, in weight percent:

Mg	3.0 - 6.0
Mn	0.5 - 2.0
Ti	< 0.2
Fe	< 0.15
Si	1.4 - 3.5

balance aluminium and impurities.

The alloy may be used in a die-casting operation, and appears to be particularly suitable for use in thixocasting and rheocasting operations.

[0005] WO-96/25528 discloses a casting alloy consisting of, in weight percent:

Mg	2.5 - 4.5, preferably 2.7 - 3.0
Mn	< 0.6, preferably 0.2 - 0.6
Fe	< 0.6
Si	< 0.45
Cu	< 0.10
Be	< 0.003, preferably < 0.001

balance aluminium and impurities.

Optionally the alloy may further comprise 0.01 - 0.04 % Ti and/or 0.01 - 0.10 % Zn.

The alloy can be employed in die-casting operations, the alloy is capable of having a yield strength greater than or equal to 110 MPa and an elongation greater than or equal to 17%.

[0006] WO-96/30554 discloses a casting alloy consisting of, in weight percent:

Mg	2.0 - 5.0, preferably 2.5 - 4.0
Mn	0.2 - 1.6, preferably 0.4 - 0.8
Zr	0.1 - 0.3
Fe	< 1.0
Si	< 0.3

balance aluminium and impurities.

The alloy may be used in die-casting operations. The casting alloy is particularly suitable for manufacturing safety components for cars. Typical strength levels disclosed in a T5-temper are YS of 116 MPa and UTS of 219 MPa and elongation of 19%.

[0007] JP-A-09-003582 discloses an aluminium casting alloy having, in weight percent:

Mg	3.0 - 5.5
Zn	1.0 - 2.0, such that Mg/Zn-ratio is 1.5 - 5.5
Mn	0.05 - 1.0
Cu	0.05 - 0.8
Fe	0.10 - 0.8

balance aluminium and inevitable impurities.

The cast products have in its matrix dispersed crystallised products in a spheroidising way.

[0008] It is an object of this invention to provide an aluminium-magnesium alloy that can be used in a variety of casting operations.

[0009] It is another object of this invention to provide an aluminium-magnesium alloy ideally suited for use in die-casting operations.

[0010] It is also an object of this invention to provide improved cast products and components consisting of an improved aluminium-magnesium alloy cast members that ideally are suited for automotive applications.

[0011] It is also an object of this invention to provide an aluminium-magnesium alloy having in the as-cast condition the following minimum mechanical properties: yield strength of at least 120 MPa, a tensile strength of at least 180 MPa and an elongation of at least 7%.

[0012] According to the invention there is provided an aluminium-magnesium casting alloy, having the following composition in weight percent:

Mg	2.7 - 6.0
Mn	0.4 - 1.4
Zn	0.10-1.5
Zr	0.3 max.
V	0.3 max.
Sc	0.3 max.
Ti	0.2 max.
Fe	1.0 max.
Si	1.4 max.

balance aluminium and inevitable impurities.

[0013] By the invention cast products or cast bodies can be provided having higher strength in combination with higher elongation. In addition these products have a good corrosion resistance and can be welded using known welding techniques for this type of casting alloys. Alloys of the present invention have also been found with a good castability, in particular in die-casting operations, and no soldering occur when using the casting alloy. The aluminium casting alloy according to the invention is capable of achieving in the as-cast condition a yield strength of more than 140 MPa, in combination with a tensile strength of more than 200 MPa and an elongation at fracture of more than 7%.

[0014] The invention also consists in products made from the aluminium casting alloy set out above. Typical examples of such products are die-cast, in particular high pressure die-cast, products such as safety components, vehicle wheels, steering wheels, steering columns, airbag modules/cans, brake drums and frame members for a vehicle. The alloy is particularly suited for any application having load and impact requirements where properties of high strength and high elongation are desirable.

[0015] The present aluminium-magnesium alloy is environmentally friendly and is readily recyclable because it does not contaminate the wrought alloy stream of recycled materials. The alloy is typically solidified into ingot-derived stock by continuous casting or semi-continuous casting into a shape suitable for remelt for casting, which shape is typically an ingot billet.

[0016] It should be mentioned here that from WO-97/38146 an aluminium wrought alloy is known for application as rolled sheet or plate or as an extrusion, and having a composition, in weight percent:-

Mg	5.0 - 6.0, preferably 5.0 - 5.6, and more preferably 5.2 - 5.6
Mn	>0.6 - 1.2, preferably 0.7 - 0.9
Zn	0.4 - 1.5
Zr	0.05 - 0.25
Cr	0.3 max.
Ti	0.2 max.
Fe	0.5 max.
Si	0.5 max.
Cu	0.4 max.
Ag	0.4 max.

balance Al and inevitable impurities.

The aluminium wrought alloy disclosed in this international patent application is also subject of the Aluminium Asso-

ciation registration number AA5069.

[0017] And from WO-99-42627 an aluminium-magnesium alloy in the form of a rolled product or an extrusion is known, having the following composition, in weight percent:-

Mg	> 3.0 - 4.5, preferably 3.5 - 4.5
Mn	0.4 - 1.2,
Zn	0.4 - 1.7, preferably 0.4 - 0.75
Zr	0.05 - 0.25
Cr	0.3 max.
Ti	0.2 max.
V	0.2 max.
Li	0.5 max.
Sc	0.5 max.
Fe	0.5 max., such that preferably Fe/Mn ratio is 0.3-1.0
Si	0.5 max.
Cu	0.15 max.
Ag	0.4 max.

balance Al and inevitable impurities.

However, neither in WO-97/38146, nor in WO-99/42627 it is mentioned or suggested that the aluminium wrought alloy could be successfully used as an aluminium casting alloy, in particular as an aluminium die-casting alloy.

[0018] It is believed that the improved properties available with the casting alloy of the invention, particularly higher strength levels and high elongation in combination with good casting characteristics, result from the combined additions of Mg, Mn and Zn in the given ranges. The aluminium casting alloy is therefore ideally suited for the improved post casting processing, i.e. the elimination of conventional high temperature solution heat treating and optionally ageing at room temperature or elevated temperature, while providing even complexly shaped die-cast products with improved dimensional stability and mechanical properties.

[0019] The reasons for the limitations of the alloying elements of the aluminium casting alloy according to the present invention are described below. All composition percentages are by weight.

[0020] Mg is the primary strengthening element in the alloy. Depending on the field of application, the magnesium content is preferably in the range of 2.7 to 6.0 %. Mg levels below 2.7% do not provide the required strength and when the addition exceeds 6.0%, problems during casting occur. A more preferred minimum Mg level is 3.0%. The preferred level of Mg is 4.5 to 6.0 %, more preferably 5.0 to 6.0 %, and most preferably 5.2 to 5.8 %, as a compromise between ease of casting, strength and corrosion resistance.

In another embodiment the Mg-level is in the range of 2.7 to 4.5%, and preferably 3.0 to 4.5%. In this range and in combination with the other alloying elements, the aluminium casting alloy is capable of obtaining in the as-cast condition an UTS of at least 210 MPa, an YS of at least 120 MPa, and an elongation of at least 17 %, and in the best examples an elongation of 23% or more.

[0021] Mn is an essential additive element. In combination with Mg and Zn, Mn provides the strength in the as-cast condition and the welded joints of the alloy. Mn levels below 0.4 % cannot provide sufficient strength and corrosion resistance to the alloy. Above 1.4 % the castability becomes increasingly difficult. The preferred level of Mn is 0.45 to 1.2 %, and more preferably 0.45 to 0.8 %, which represents a balanced compromise between strength, corrosion resistance, and castability.

[0022] Zn is also an essential alloying element. In combination with Mg, Zn provides the strength in the as-cast condition and the welded joints of the alloy. Furthermore, the addition of Zn results in a good corrosion resistance of the aluminium cast alloy. Zn should be present in a range of 0.10 to 1.5%. At a level above 1.5% Zn the castability becomes increasingly difficult. A preferred range for Zn is 0.3 to 1.4 %, more preferably 0.4 to 1.1 %, and most preferably 0.45 to 0.9 %, which represents a compromise between strength, corrosion resistance and castability. Usually Zn is considered in the art as an impurity element in AlMg casting alloys, which should be kept at a level as low as possible, preferably maximum of 0.10 % and more preferably maximum of 0.05 %. However, in the alloy according to the invention Zn may be present as an alloying element resulting in beneficial effects. Although not yet fully understood, it is believed that the addition of Zn contributes to the good casting characteristics of the alloy, such as a low tendency to die-sticking when used in a die-casting operation. Good results are being achieved in those examples having a Mg/Zn-ratio of 6.0 or more.

[0023] Zr is for achieving strength improvement in the cast product. Zr also improves the weldability of the cast product. Zr levels above 0.3 % tend not to have any further advantages. The preferred level of Zr is in the range of

0.05 to 0.25 %, and more preferably 0.06-0.16%.

[0024] V may be added for achieving further improvements in the mechanical properties of the cast product, in particular mechanical properties at elevated temperatures. If added, the preferred level of V is in the range of 0.05 to 0.25 %, and more preferably in the range of 0.1 to 0.2 %. The addition of V in the given range may in particular result in a further improved ductility of the alloy, in particular when heat treated following casting at a temperature in a range of 200 to 400°C.

[0025] Sc may be added to the alloy for improving the weldability of a cast product. The Sc may be added alone or in combination with Zr in a range of 0.05 to 0.25 %. When Sc is added the resultant cast product should be heat treated preferably following the casting operation by holding the cast product at a temperature in a range of 250 to 400°C for a holding time up to 10 hours. The Sc level should not exceed 0.3 %, and is preferably in a range of 0.05 to 0.2 %.

[0026] Further optional alloying element in the alloy according to the invention to improve specific properties can be up to 0.6 % Cobalt alone or in combination with up to 0.6 % Cerium, and Strontium up to 0.04 %.

[0027] Ti is important as a grain refiner during solidification of both cast products and welded joint produced using the alloy of the invention. A preferred maximum for Ti addition is 0.2 %, and where a more preferred range is of 0.01 to 0.14 %.

[0028] Fe is a known element in aluminium casting alloys and may be present in a range up to 1.0%. At higher levels Fe may form undesirable large compounds with Mn in the holding furnaces typically employed in casting operations. When higher fracture toughness and/or ductility is desired a suitable maximum for the Fe content is 0.5 %, and more preferably 0.3 %, and most preferably 0.2 %.

[0029] Si is a known impurity element in aluminium casting alloys, and normally should not be present at too high levels to avoid the loss in primary strengthening element Mg. However, in the present aluminium casting alloy it can be present in a range of up to 1.4 %. Although at higher Si-levels the elongation is somewhat reduced, still very acceptable high levels of elongation in combination with high strength levels are obtained. In a preferred embodiment the Si level should not be more than 1.0 %, and more preferably not more than 0.5 %, and most preferably not more than 0.3 %. A suitable minimum Si-level is 0.10 %, and more preferably 0.15%.

[0030] Be may be added to AlMg casting alloys to prevent oxidation of the magnesium in the aluminium alloy, the amount added varying with the magnesium content of the alloy. As little as up to 0.005% causes a protective beryllium oxide film to form on the surface. Preferably, the Be level has a maximum of 0.005%, and more preferably is absent without deteriorating the properties of the cast product with this aluminium alloy.

[0031] The balance is aluminium and inevitable impurities. Typically each impurity is present at 0.05 % maximum and the total of impurities is 0.25 %.

[0032] In an embodiment of the aluminium casting alloy according to the invention the alloy is capable of achieving in the as-cast condition a yield strength of more than 160 MPa, and in the best examples of more than 175 MPa, in combination with a tensile strength of more than 250 MPa, preferably more than 280 MPa, and in combination with an elongation of more than 10%, and in the best examples even more than 12%. By optimising the casting parameters, further improved tensile properties, and in particular in elongation, can be obtained. Furthermore, improvements in the mechanical properties of the alloy according to the invention can be obtained heat-treating a cast product as is conventional in the art. This further improvement is achieved at the expense of the loss of the earlier advantage that following casting no further heat treatments are required to achieve a desirable level of mechanical properties.

[0033] In another embodiment of the aluminium casting alloy according to the invention the alloy is capable of achieving in the as-cast condition a yield strength of more than 120 MPa, and in the best examples of more than 140 MPa, in combination with a tensile strength of more than 210 MPa, preferably more than 240 MPa, and in combination with an elongation of more than 17%, and in the best examples even more than 23%. By optimising the casting parameters, further improved tensile properties, and in particular in elongation, can be obtained. Furthermore, improvements in the mechanical properties of the alloy according to the invention can be obtained heat-treating a cast product as is conventional in the art. This further improvement is achieved at the expense of the loss of the earlier advantage that following casting no further heat treatments are required to achieve a desirable level of mechanical properties.

[0034] The aluminium-magnesium casting alloy in accordance with the invention may be processed by applying various casting techniques. The best advantages are being achieved when applied via permanent mould casting, die-casting, or squeeze casting. In particular when die-casting processes are applied, including vacuum die-casting processes, the best combination of desirable properties and castability characteristics is being obtained. It is believed that by applying vacuum die-casting the weldability characteristics of the alloy according to the invention may be further improved. It is to be understood here that die-casting includes high-pressure die-casting operations.

[0035] In another aspect of the invention there is provided in a method of producing an cast aluminium product, preferably a die-cast product, comprising the aluminium alloy of the invention as set out above, and casting, preferably die-casting, a body of said aluminium alloy. Following the casting operation the (die-)cast body can be aged at a temperature in the range of 140 to 250°C for a soaking time at this temperature in the range of 0.5 to 24 hours.

[0036] The invention will now be explained by reference to non-limiting examples.

7250°C - 4000 !!! A.M.

Example 1.

[0037] On an industrial scale of casting two AlMg-alloys according to the invention, see Table 1, have been die-cast on a Mueller-Weingarten cold-chamber-die-casting machine with a locking pressure of 2 MN. The casting parameters varied comprised the preheat temperature of the die (130°C and 210°C) and the backpressure (500 and 900 bar). The die-cast product consisted of a plate having dimensions 100x150x2 mm.

[0038] From this die-cast plate three tensile specimen have been machined and subsequently tested in the as-cast condition. The mechanical properties in the as-cast condition averaged over three specimen tested have been listed in Table 2, where YS stands for 0.2% yield strength and UTS for ultimate tensile strength. The elongation corresponds to the German norm A5. The AlMg-alloy according to the invention showed during the die-casting operation no tendency to die-sticking.

[0039] From the results in Table 2 it can be seen that the AlMg-alloy according to the invention results in very high tensile properties and high elongation in the as-cast condition. These surprisingly high properties are achieved without the need for further heat treatments. In particular the UTS and the elongation can be improved by increasing the backpressure in the casting operation. Smaller improvements in mechanical properties can be obtained by increasing the die-temperature. Further improvements can be expected by optimising the casting conditions, in particular by applying vacuum (high pressure) die-casting instead of conventional (high pressure) die-casting. From the results of alloy 2 it can be seen that having a high Si-level may still result in a very acceptable elongation in combination with very high tensile strengths.

Table 1.

Alloy	Alloying and impurity elements, in wt.%							
	Si	Fe	Cu	Mn	Mg	Zn	Ti	Zr
1	0.34	0.23	0.005	0.54	5.8	0.51	0.01	0.11
2	1.20	0.30	0.005	0.54	5.7	0.58	0.01	0.12

Table 2.

Alloy	Die-casting parameter applied	Mechanical property as-cast condition		
		YS [MPa]	UTS [MPa]	Elongation [%]
1	130°C/500bar	172	276	7.3
1	210°C/500 bar	168	278	8.3
1	130°C/900 bar	171	301	13.0
1	210°C/900 bar	170	305	14.2
2	130°C/500bar	178	293	7.0
2	210°C/500 bar	181	288	7.0
2	130°C/900 bar	185	312	11.1
2	210°C/900 bar	188	313	9.2

Example 2.

[0040] On an industrial scale of casting four AlMg-alloys according to the invention, see Table 3, have been cast on a GDK-750 Mueller-Weingarten Vacural-cold-chamber-die-casting machine with a locking pressure of 8500 kN. The casting parameters comprised a preheat temperature of the die of 250°C and a backpressure of 500 bar. The vacuum die-cast products consisted of a plate having dimension 200x250x2 mm and 200x250x4 mm, hereinafter referred to as 2mm and 4mm plates respectively.

[0041] From each alloy six 2mm or 4 mm plates have been cast. And from each die-cast plates a tensile specimen has been machined and subsequently tested in the as-cast condition. The mechanical properties in the as-cast condition averaged over six specimen tested have been listed in Table 4, where YS stands for 0.2% yield strength and UTS for ultimate tensile strength. The elongation corresponds to the German norm A5. The AlMg-alloy according to the invention showed during the die-casting operation no tendency to die-sticking.

[0042] From the results in Table 4 it can be seen that the AlMg-alloy according to the invention results in very high tensile properties and high elongation in the as-cast condition. From the results of Table 4 it can be seen that AlMg-alloys 2 and 3 having a fairly low Mg-level in combination with the Zn and Mn-levels, combine good strength levels with very high elongation. Except for the minor difference in Mg-content, alloys 2 and 3 have essentially the same composition. The difference in mechanical properties are believed to be due to the difference in plate thickness cast, it has been found that in the experiments carried out the 2 mm plates has somewhat more casting defects than the 4 mm plates. This difference can easily be overcome by further optimising the casting conditions. It is believed that alloys 2 and 3, independent of the plate thickness, are capable of obtaining a yield strength of 120 MPa or more, a tensile strength of 210 MPa or more, and an elongation of 20% or more. In the best examples an elongation of 27% has been measured.

Table 3.

Alloy	Alloying and impurity elements, in wt.%							
	Si	Fe	Cu	Mn	Mg	Zn	Ti	Zr
1	0.20	0.27	0.03	0.47	4.9	0.47	0.01	0.12
2	0.18	0.26	0.04	0.57	3.5	0.41	0.01	0.13
3	0.20	0.28	0.04	0.51	3.2	0.42	0.01	0.13
4	0.26	0.26	0.04	0.53	5.0	0.62	0.01	0.12

Table 4.

Alloy	Plate thickness	Mechanical properties in the as-cast condition		
		YS [MPa]	UTS [MPa]	Elongation [%]
1	4 mm	137	259	13
2	2 mm	128	247	17
3	4 mm	114	247	23
4	2 mm	149	279	15

Example 3.

[0043] The 2mm vacuum die-cast product of Example 2 having the composition of Alloy no. 3 of Table 3 has been subjected also to a welding operation, during which in particular the development of porosity has been assessed. Various welded joints have been made whereby the 2 mm die-cast plate was put on top of a 1.6 mm gauge AA6016A-wrought sheet such that an overlap was created ("Überlappverbindung"). At the overlap a weld was made by means of automated TIG welding, in a single pass and using 1.2 mm filler wire of AlSi12 (DIN 1732). Following welding the porosity in the welds has been determined using standard metallographic assessment techniques. An important criteria of a large European car manufacturer is that the level of porosity, as assessed by the square area occupied by the poros, must be 8% or less in order to qualify the weld as acceptable. Furthermore the pore size must be smaller than 0.5 times the thinnest welded sheet used, and only the pores that are larger than 0.05 mm should be taken into account. In the welds using the die-cast alloy according to the invention the average porosity level was always in the range of 0.5 to 2.0%. No large pore sizes (> 0.8 mm) have been found. This qualifies the die-casting alloy as being very good weldable.

Claims

1. An aluminium-magnesium alloy for casting operations consisting of, in weight percent:-

Mg	2.7 - 6.0
Mn	0.4-1.4
Zn	0.10 - 1.5
Zr	0.3 max.

(continued)

V	0.3 max.
Sc	0.3 max.
Ti	0.2 max.
Fe	1.0 max.
Si	1.4 max.

impurities each 0.05 max.
total 0.25 max.
balance aluminium.

2. An aluminium casting alloy according to claim 1, wherein the Mg content is in the range of 4.5 to 6.0 %, and preferably in the range of 5.0 to 6.0%.
3. An aluminium casting alloy according to claim 1, wherein the Mg content is in the range of 2.7 to 4.5 %, and preferably in the range of 3.0 to 4.5%.
4. An aluminium casting alloy according to any one of claims 1 to 3, wherein the Fe content is in the range of up to 0.5 %.
5. An aluminium casting alloy according to any one of claims 1 to 4, wherein the Mn content is in the range of 0.4 to 1.2 %.
6. An aluminium casting alloy according to any one of claims 1 to 5, wherein the Zn content is in the range of 0.3 to 1.4%, preferably in the range of 0.4 to 1.1 %.
7. An aluminium casting alloy according to any one of claims 1 to 6, wherein the Zr content is in the range of 0.05 to 0.25 %.
8. An aluminium casting alloy according to any one of claims 1 to 7, wherein the aluminium casting alloy is a die-casting alloy.
9. An aluminium alloy according to claim 8, where the die-cast aluminium alloy in the as-cast condition is **characterised by** an UTS of at least 250 MPa, an YS of at least 160 MPa, and an elongation of at least 10 %.
10. Aluminium alloy according to claim 8, where the die-cast aluminium alloy in the as-cast condition is **characterised by** an UTS of at least 210 MPa, an YS of at least 120 MPa, and an elongation of at least 17 %.
11. Die-cast product of an aluminium casting alloy having a composition in accordance with any one of claims 1 to 10.
12. Use of a die-casting alloy according to any one of claims 8 to 10 for die-casting of safety components.
13. Use of a die-casting alloy according to any one of claims 8 to 10 for die-casting of a frame member for a vehicle.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 20 0977

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
D,X	PATENT ABSTRACTS OF JAPAN vol. 1997, no. 05, 30 May 1997 (1997-05-30) -& JP 09 003582 A (SUMITOMO LIGHT METAL IND LTD), 7 January 1997 (1997-01-07) * abstract; example 15; table 2 *	1-6, 8-11	C22C21/06 C22C21/08
A	---	12, 13	
X	PATENT ABSTRACTS OF JAPAN vol. 1997, no. 06, 30 June 1997 (1997-06-30) -& JP 09 041064 A (MITSUBISHI ALUM CO LTD), 10 February 1997 (1997-02-10) * abstract; examples 3, 12; tables 1, 2 *	1, 3-6	
A	---	9, 10, 12, 13	
E	WO 00 26020 A (HASZLER ALFRED JOHANN PETER ; HOOGOVENS ALU WALZPROD GMBH (DE); MEC) 11 May 2000 (2000-05-11) * page 12; example 1 * * claims 5, 11 *	1, 2, 4-7	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
X	EP 0 799 900 A (HOOGOVENS ALU WALZPROD GMBH) 8 October 1997 (1997-10-08) * the whole document * * claim 2 *	1, 2, 4-7	C22C
A	---	8-13	
D,X	WO 97 38146 A (HOOGOVENS ALU WALZPROD GMBH ; HASZLER ALFRED JOHANN PETER (DE); SAM) 16 October 1997 (1997-10-16) * the whole document * * examples B7, B11, B13; table 1 * * table 3 *	1, 2, 4-7	
A	---	8-13	
	--- -/--		
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 27 April 2001	Examiner Lilimpakis, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04001)

BEST AVAILABLE COPY



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 20 0977

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
D,X	WO 99 42627 A (HASZLER ALFRED JOHANN PETER ;HOOGOSENS ALU WALZPROD GMBH (DE); SAM) 26 August 1999 (1999-08-26) * examples 4,5,7; table 1 *	1,3-7	
A	-----	8-13	
X	WO 99 17903 A (HASZLER ALFRED JOHANN PETER ;HOOGOSENS ALU WALZPROD GMBH (DE); SAM) 15 April 1999 (1999-04-15) * claim 1; example 1; table 1 *	1,2,4-7	
X	FR 2 731 019 A (PECHINEY RHENALU) 30 August 1996 (1996-08-30) * page 5; examples 8,9 *	1,2,4	
A	PATENT ABSTRACTS OF JAPAN vol. 013, no. 260 (C-607), 15 June 1989 (1989-06-15) -& JP 01 062435 A (FURUKAWA ALUM CO LTD), 8 March 1989 (1989-03-08) * abstract; example 3; table 1 *	1-6	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
Place of search MUNICH		Date of completion of the search 27 April 2001	Examiner Lilimpakis, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (7-04-C01)

BEST AVAILABLE COPY

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 20 0977

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-04-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 09003582 A	07-01-1997	NONE	
JP 09041064 A	10-02-1997	NONE	
WO 0026020 A	11-05-2000	AU 1268100 A	22-05-2000
EP 0799900 A	08-10-1997	AT 197317 T	15-11-2000
		AU 2293397 A	29-10-1997
		BR 9708513 A	04-01-2000
		CA 2250977 A	16-10-1997
		CN 1217030 A, B	19-05-1999
		DE 69703441 D	07-12-2000
		DE 69703441 T	19-04-2001
		WO 9738146 A	16-10-1997
		EP 0892858 A	27-01-1999
		ES 2153189 T	16-02-2001
		JP 11507102 T	22-06-1999
		NO 984634 A	02-10-1998
WO 9738146 A	16-10-1997	EP 0799900 A	08-10-1997
		AT 197317 T	15-11-2000
		AU 2293397 A	29-10-1997
		BR 9708513 A	04-01-2000
		CA 2250977 A	16-10-1997
		CN 1217030 A, B	19-05-1999
		DE 69703441 D	07-12-2000
		DE 69703441 T	19-04-2001
		EP 0892858 A	27-01-1999
		ES 2153189 T	16-02-2001
		JP 11507102 T	22-06-1999
		NO 984634 A	02-10-1998
WO 9942627 A	26-08-1999	AU 2725799 A	06-09-1999
		EP 1078109 A	28-02-2001
		NO 20004154 A	18-08-2000
WO 9917903 A	15-04-1999	AU 1148999 A	27-04-1999
		BR 9812608 A	01-08-2000
		CN 1272810 T	08-11-2000
		EP 1019217 A	19-07-2000
		NO 20001686 A	31-03-2000
		ZA 9809015 A	13-04-1999
FR 2731019 A	30-08-1996	FR 2731018 A	30-08-1996
		AU 690433 B	23-04-1998
		AU 4930596 A	11-09-1996

EPO FORM P0469

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

BEST AVAILABLE COPY

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 20 0977

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-04-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2731019 A		AU 7308598 A	27-08-1998
		CA 2211433 A	29-08-1996
		CN 1175983 A	11-03-1998
		DE 804626 T	29-01-1998
		EP 0804626 A	05-11-1997
		EP 0909828 A	21-04-1999
		FI 963290 A	25-08-1996
		WO 9626299 A	29-08-1996
		JP 11500783 T	19-01-1999
		NO 973681 A	11-08-1997
		NZ 302706 A	29-04-1999
		PL 321887 A	22-12-1997
		TR 9700843 T	21-02-1998
JP 01062435 A	08-03-1989	NONE	

EPO FORM PM459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

BEST AVAILABLE COPY